



Law

PTO/SB/21 (11-07)

Approved for use through 11/30/2007. OMB 0651-0031  
U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

## TRANSMITTAL FORM

(to be used for all correspondence after initial filing)

Total Number of Pages in This Submission

2

Application Number	10/771,334
Filing Date	02-05-2004
First Named Inventor	Roland FULFORD
Art Unit	1714
Examiner Name	Edward J. CAIN
Attorney Docket Number	DSM 16267-8

### ENCLOSURES (Check all that apply)

- |   |   |   |
|---|---|---|
| <input type="checkbox"/> Fee Transmittal Form<br><input type="checkbox"/> Fee Attached<br><input type="checkbox"/> Amendment/Reply<br><input type="checkbox"/> After Final<br><input type="checkbox"/> Affidavits/declaration(s)<br><input type="checkbox"/> Extension of Time Request<br><input type="checkbox"/> Express Abandonment Request<br><input type="checkbox"/> Information Disclosure Statement<br><input checked="" type="checkbox"/> Certified Copy of Priority Document(s) 1<br><input type="checkbox"/> Reply to Missing Parts/<br>Incomplete Application<br><input type="checkbox"/> Reply to Missing Parts<br>under 37 CFR 1.52 or 1.53 | <input type="checkbox"/> Drawing(s)<br><input type="checkbox"/> Licensing-related Papers<br><input type="checkbox"/> Petition<br>Petition to Convert to a<br>Provisional Application<br><input type="checkbox"/> Power of Attorney, Revocation<br>Change of Correspondence Address<br><input type="checkbox"/> Terminal Disclaimer<br><input type="checkbox"/> Request for Refund<br><input type="checkbox"/> CD, Number of CD(s) _____<br><input type="checkbox"/> Landscape Table on CD | <input type="checkbox"/> After Allowance Communication to TC<br><input type="checkbox"/> Appeal Communication to Board<br>of Appeals and Interferences<br><input type="checkbox"/> Appeal Communication to TC<br>(Appeal Notice, Brief, Reply Brief)<br><input type="checkbox"/> Proprietary Information<br><input type="checkbox"/> Status Letter<br><input type="checkbox"/> Other Enclosure(s) (please identify<br>below): Remarks |
|---|---|---|

Remarks

### SIGNATURE OF APPLICANT, ATTORNEY, OR AGENT

Firm Name BERESKIN & PARR

Signature

Printed name

David St-Martin

Date

December 7, 2007

Reg. No.

58225

### CERTIFICATE OF TRANSMISSION/MAILING

I hereby certify that this correspondence is being facsimile transmitted to the USPTO or deposited with the United States Postal Service with sufficient postage as first class mail in an envelope addressed to: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450 on the date shown below:

Signature

Typed or printed name

Date

This collection of information is required by 37 CFR 1.5. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.11 and 1.14. This collection is estimated to take 2 hours to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

If you need assistance in completing the form, call 1-800-PTO-9199 and select option 2.



## Privacy Act Statement

The Privacy Act of 1974 (P.L. 93-579) requires that you be given certain information in connection with your submission of the attached form related to a patent application or patent. Accordingly, pursuant to the requirements of the Act, please be advised that: (1) the general authority for the collection of this information is 35 U.S.C. 2(b)(2); (2) furnishing of the information solicited is voluntary; and (3) the principal purpose for which the information is used by the U.S. Patent and Trademark Office is to process and/or examine your submission related to a patent application or patent. If you do not furnish the requested information, the U.S. Patent and Trademark Office may not be able to process and/or examine your submission, which may result in termination of proceedings or abandonment of the application or expiration of the patent.

The information provided by you in this form will be subject to the following routine uses:

1. The information on this form will be treated confidentially to the extent allowed under the Freedom of Information Act (5 U.S.C. 552) and the Privacy Act (5 U.S.C. 552a). Records from this system of records may be disclosed to the Department of Justice to determine whether disclosure of these records is required by the Freedom of Information Act.
2. A record from this system of records may be disclosed, as a routine use, in the course of presenting evidence to a court, magistrate, or administrative tribunal, including disclosures to opposing counsel in the course of settlement negotiations.
3. A record in this system of records may be disclosed, as a routine use, to a Member of Congress submitting a request involving an individual, to whom the record pertains, when the individual has requested assistance from the Member with respect to the subject matter of the record.
4. A record in this system of records may be disclosed, as a routine use, to a contractor of the Agency having need for the information in order to perform a contract. Recipients of information shall be required to comply with the requirements of the Privacy Act of 1974, as amended, pursuant to 5 U.S.C. 552a(m).
5. A record related to an International Application filed under the Patent Cooperation Treaty in this system of records may be disclosed, as a routine use, to the International Bureau of the World Intellectual Property Organization, pursuant to the Patent Cooperation Treaty.
6. A record in this system of records may be disclosed, as a routine use, to another federal agency for purposes of National Security review (35 U.S.C. 181) and for review pursuant to the Atomic Energy Act (42 U.S.C. 218(c)).
7. A record from this system of records may be disclosed, as a routine use, to the Administrator, General Services, or his/her designee, during an inspection of records conducted by GSA as part of that agency's responsibility to recommend improvements in records management practices and programs, under authority of 44 U.S.C. 2904 and 2906. Such disclosure shall be made in accordance with the GSA regulations governing inspection of records for this purpose, and any other relevant (i.e., GSA or Commerce) directive. Such disclosure shall not be used to make determinations about individuals.
8. A record from this system of records may be disclosed, as a routine use, to the public after either publication of the application pursuant to 35 U.S.C. 122(b) or issuance of a patent pursuant to 35 U.S.C. 151. Further, a record may be disclosed, subject to the limitations of 37 CFR 1.14, as a routine use, to the public if the record was filed in an application which became abandoned or in which the proceedings were terminated and which application is referenced by either a published application, an application open to public inspection or an issued patent.
9. A record from this system of records may be disclosed, as a routine use, to a Federal, State, or local law enforcement agency, if the USPTO becomes aware of a violation or potential violation of law or regulation.



Office de la propriété  
intellectuelle  
du Canada

Un organisme  
d'Industrie Canada

Canadian  
Intellectual Property  
Office

An Agency of  
Industry Canada

*Bureau canadien  
des brevets  
Certification*

*Canadian Patent  
Office  
Certification*

La présente atteste que les documents  
ci-joints, dont la liste figure ci-dessous,  
sont des copies authentiques des docu-  
ments déposés au Bureau des brevets.

This is to certify that the documents  
attached hereto and identified below are  
true copies of the documents on file in  
the Patent Office.

Certified to be a true and correct copy of International Application No: **PCT/CA02/01233**,  
filed August 8, 2002.

*L. Lechance*  
Agent certificateur/Certifying Officer

December 5, 2007

Date

Canada

(CIPO 68)  
31-03-04

OPIC  CIPO

ABSTRACT

The invention relates to a process for converting an elastomer from scrap to a regenerated elastomer which comprises the steps of: a) introducing the elastomer from scrap into a vessel equipped with agitating means, the elastomer from scrap being in a powder form; b) agitating and heating the elastomer from scrap, limiting the heating of the elastomer from scrap to a temperature below the temperature where the elastomer begins to degrade; c) introducing an oil into the vessel and admixing together the elastomer from scrap and the oil; and d) cooling down the so formed regenerated elastomer, whereby the regenerated elastomer has properties similar to a corresponding virgin elastomer. A regenerated elastomer and its use are also disclosed.

## PROCESS FOR REGENERATION OF RUBBER FROM SCRAP

### BACKGROUND OF THE INVENTION

#### 1. Field of the Invention

5           The present invention relates to improvements in the field of recycled rubber. More particularly, the invention relates to a process for converting a rubber from scrap to a regenerated rubber.

#### 2. Description of the Prior Art

10           Recycling of elastomers in general and more particularly recycling of rubber constitute a major concern from a social and environmental view. As little progress in the production of high quality rubber products derived from vulcanized rubber has failed to meet the quality required by the industry, the current situation calls for the development of new technologies, to show the ability to expand a very demanding market by producing a larger number of high quality and competitive products derived from scrap  
15 rubber. This can be achieved if the recycled elastomer or rubber is processed with the same conventional processing methods as for virgin elastomer or rubber.

          There are several major markets in use today for the recycling of elastomers from scrap, rubber from scarp, tire derived fuel, punched or stamped products from tire carcasses, mats and many low end applications using bonding technologies of the rubber  
20 particles. However, those issues that deal with reclaimed rubber derived from some chemical treatment of vulcanized rubber hold a promising alternative to a durable solutions. Various patented methods are claiming a successful chemical partial devulcanization of scrap rubber using a chemical treatment that involves thermal, mechanical energy or other form of energy such as ultra sonic. Devulcanization is defined  
25 as a reverse reaction of the sulfur carbon bonding. Unfortunately, large-scale commercial applications of those methods are prohibited either from an economical point of view or in regard to the poor properties of the products obtained from the processes proposed.

## SUMMARY OF THE INVENTION

It is therefore an object of the invention to provide a process for converting an elastomer from scrap to a regenerated elastomer. It is another object of the present invention to provide a regenerated elastomer having properties similar to a corresponding virgin elastomer.

According to a first aspect of the invention, there is provided a process for converting an elastomer from scrap to a regenerated elastomer which comprises the steps of:

- a) introducing the elastomer from scrap into a vessel equipped with agitating means, the elastomer from scrap being in a powder form;
- b) agitating and heating the elastomer from scrap, limiting the heating of the elastomer from scrap to a temperature below the temperature where the elastomer begins to degrade;
- c) introducing an oil into the vessel and admixing together the elastomer from scrap and the oil; and
- d) cooling down the so formed regenerated elastomer, whereby the regenerated elastomer has properties similar to a corresponding virgin elastomer.

The term "elastomer" as used herein refers to a crosslinked polymer having a structure forming a network where the chains of the polymer are joined together. This term is used as a broader term than rubber since in many cases rubbers can also comprise other additives such as filling agents and vulcanizing agents.

According to a second aspect of the invention, there is provided a regenerated elastomer obtained via the process described in the first aspect of the invention or in any of its preferred embodiments.

Applicant has found quite surprisingly that by agitating and heating an elastomer from scrap prior to admixing it with a preheated oil, it is possible to convert the elastomer from scrap to a regenerated elastomer and avoid its degradation. Also, the applicant has found that by using such a process, the obtained regenerated elastomer is an expanded and soft powder which is non-sticky and non-masticated or unmasticated. The regenerated elastomer does not soil hands by touch and has a characteristic velvet touch. Furthermore, the regenerated elastomer has properties similar to a corresponding virgin elastomer. During experiments, it was demonstrated that the regenerated elastomer is

compatible with the corresponding virgin elastomer and it has a similar polymer content. Thus, in elastomer compounds, the regenerated elastomer could replace a portion of the virgin elastomer normally used without affecting the properties of the compound.

#### DESCRIPTION OF THE PREFERRED EMBODIMENTS

5 In a preferred embodiment of the process according to the first aspect of the invention, the vessel can be a vessel of the double boiler type. Preferably, the boiler comprises a mixing chamber and a heating chamber. Agitating means preferably comprises a rotor having at least one blade mounted on a central shaft. The agitation of the elastomer from scrap can be brought by rotating the rotor to generate shearing forces.  
10 Preferably, the rotor is rotated at a revolution comprised between 150 and 1200 rpm and more preferably comprised between 160 and 200 rpm. The elastomer from scrap can be converted to the regenerated elastomer in a period of time comprised between 30 seconds and 20 minutes, preferably comprised between 5 minutes and 15 minutes and more preferably of about 10 minutes.

15 In another preferred embodiment of the process according to the first aspect of the invention, the vessel is preferably a mixer and more preferably a thermokinetic mixer. The elastomer from scrap can be heated from the heat generated through thermokinetic energy produced by the agitation. The agitating means preferably comprises a rotor having at least one blade mounted on a central shaft. The agitation of  
20 the elastomer from scrap can be brought by rotating the rotor to generate shearing forces. The rotor can be rotated at a revolution comprised between 1500 and 3000 rpm and preferably comprised between 1800 and 2000 rpm. The elastomer from scrap can be converted to the regenerated elastomer in a period of time comprised between 30 seconds and 5 minutes, preferably comprised between 45 seconds and 3 minutes and more  
25 preferably of about 1 minute.

#### Vessel

In the process according to the first aspect of the invention, the vessel can be equipped with a temperature control device comprising a heating system. The temperature control device can further comprise a cooling system.

#### 30 Additional steps

According to the first aspect of the invention, the process can further comprise after step (b) and prior to step (c):

b') stopping the agitation

and the agitation is started again in step (c), after the introduction of the oil into the vessel. The process can also further comprise after step (c) and prior to step (d):

c') ejecting the regenerated elastomer from the vessel.

#### 5 Temperature

In the process according to the first aspect of the invention, the elastomer form scrap is preferably heated at a temperature  $t_1$  comprised between 50 and 200 °C, more preferably comprised between 140 and 170 °C and even more preferably at about 160 °C.

#### 10 Particle size

In the process according to the first aspect of the invention, the powder can have a particle size of about 15 to about 200 mesh, preferably of about 20 to about 120 mesh and more preferably of about 80 to 100 mesh. The powder can also be constituted by at least 90 % of particles having a size of at least 15 mesh and preferably of at least 30 mesh. The powder can further be constituted by at least 99 % of particles having a size of at least 15 mesh and preferably of at least 30 mesh.

#### Agitation

In the process according to the first aspect of the invention, the agitation is preferably carried out to avoid having stagnant particles of the elastomer in the vessel. The agitation can also be carried out to evenly heat the elastomer from scrap and therefore prevent its degradation. The agitation can be maintained during step (c) and preferably, also during step (d).

#### Oil

In the process according to the first aspect of the invention, the weight ratio, oil / elastomer from scrap, can be comprised between 0.03 and 0.2, preferably comprised between 0.04 and 0.14 and more preferably comprised between 0.05 and 0.09. The oil is preferably preheated prior to admixing and preferably at a temperature  $t_2$  being higher or equal to  $t_1$ . The temperature  $t_2$  can also have a value comprised between  $t_1$  and  $t_1+60$  °C and preferably comprised between  $t_1+10$  and  $t_1+40$  °C. The oil can be selected from the group consisting of synthetic oil, vegetable oil and mixtures thereof. The oil is preferably synthetic oil and more preferably selected from the group consisting of aromatic oil,



naphtenic oil, paraffinic oil and mixtures thereof. When use is made of a paraffinic oil, the elastomer from scrap is preferably an ethylene propylene diene monomer rubber (EPDM). When use is made of an aromatic oil or a naphthenic oil, the elastomer from scrap is preferably a styrene butadiene rubber (SBR).

#### 5 Cooling

In the process according to the first aspect of the invention, in step (d), the regenerated elastomer can be kept in continuous motion in order to avoid degradation. Step (d) is preferably carried out using a screw type cooling device which preferably comprises a temperature control device. In step (d), the regenerated elastomer is  
10 preferably cooled down to a temperature below 120°C and more preferably to a temperature comprised between 90 and 120°C, to prevent its degradation.

#### Experimental conditions of the process

The process according to the first aspect of the invention can be carried out in the presence of air. The process can also be carried out under an inert gas atmosphere  
15 and the inert gas is preferably argon or nitrogen. Preferably, the gas atmosphere is substantially free of oxygen. Preferably, the risks of a potential side reaction such as oxidation are reduced.

#### Mass recovered

In the process according to the first aspect of the invention, the quantity of  
20 regenerated elastomer obtained at the end of the process corresponds to a value comprised between 97.0 and 99.9% and preferably comprised between 98.5 and 99.5% of the combined weight of the elastomer from scrap and the oil introduced into the vessel.

#### Mastication

In the process according to the first aspect of the invention, preferably, no  
25 mastication of the elastomer from scrap or of the regenerated elastomer occurs.

#### Rubber

The elastomer from scrap, in the process according to the first aspect of the invention, is preferably a rubber from scrap.

#### Regenerated Elastomer

30 In the second aspect of the invention, the regenerated elastomer is preferably in a powder form and more preferably the regenerated elastomer has an aspect of

expanded powder. Preferably, the regenerated elastomer is an unmasticated elastomer. It also preferably does not retain moisture. The regenerated elastomer can have a velvet touch and is preferably non-sticky. Preferably, The regenerated elastomer does not soil hands by touch. The regenerated elastomer preferably comprises a quantity of oil comprised between 3 and 14 % by weight, the oil being encapsulated into the regenerated elastomer. More preferably, the quantity of said oil is comprised between 5 and 8 % by weight. Also, the regenerated elastomer preferably does not retain moisture. The regenerated elastomer can exhibit all the required characteristics needed for processing by using the methods of mixing, molding, extrusion and calendering, commonly used in the rubber industry. The regenerated elastomer can be effective in the composition of a product selected from the group consisting of gasket, hose and roofing. Also, the regenerated elastomer can be effective in the composition of hoses and car tires.

The regenerated elastomer is preferably a regenerated rubber. The regenerated rubber can have a polymer content comprised between 10 and 40% by weight and preferably comprised between 25 and 35% by weight.

#### Utilisation of the regenerated elastomer

The regenerated elastomer according to the second aspect of the invention can be used in the rubber industry. Preferably, the regenerated elastomer is, previously to its use in the rubber industry, prepared by a process selected from the group consisting of mixing, molding, extrusion, and calendering. The regenerated elastomer can be added with additives commonly used in the preparation of native rubber, previously to its use in the rubber industry. The regenerated elastomer can also be used in the composition of a product of the automobile industry. The composition preferably comprises between 1 and 40% by weight and more preferably between 25 and 35% by weight of said regenerated elastomer. It is also possible to use the regenerated elastomer in the fabrication of a hose, a gasket or a seal. The hose, the gasket or the seal preferably comprise between 1 and 40% by weight and more preferably between 25 and 35% by weight of said regenerated elastomer. The elastomer is preferably a rubber.

#### Experimental section

The following non-limiting protocols and compounds illustrate the invention.

### General procedures

The Applicant has prepared regenerated rubber according to two main procedures, Protocol A and B. Prior to treating the rubber from scrap according to any one of these two protocols, all the undesired components contained in the powder (steel, fibers, general dirt) have been removed. The experimental conditions investigated in the present work are in accordance with the definitions given in the claims.

### Protocol A

A weighted quantity of scrap rubber from scrap tires in the form of a granulated powder, having a given size of 80, 100 or 120 mesh, was introduced into a vessel of the double boiler type having a volume of 8 US gallons. The vessel is equipped with agitation means comprising a rotor having three blades mounted on a central shaft and capable of generating shearing forces. The rotor blades were adequately designed and the agitation is carried out to avoid having stagnant particles of rubber in the vessel. Thus, all rubber powder was uniformly subjected to the combination of the thermal and mechanical energies. The rotor speed was set based on the quantity, type and granulometry of the rubber powder introduced into the vessel and at a sufficient level to generate shearing forces. The powder was heated for 5 minutes until it reached a temperature comprised between 140°C and 160°C. A tight control of the temperature was necessary during the process in order to prevent any damage to the powder in the form of degradation. When all the particles have reached the required temperature, a hot oil (aromatic oil, naphtenic oil or paraffinic oil ) having a temperature of about 190 to 200°C was added in a weight ratio, oil / rubber from scrap, comprised between 0.05 and 0.12. The ratio depends on the nature and the granulometry of the powder as well as on the type of oil selected and its temperature. The mixture was kept under agitation for a period of time of about 5 minutes to allow the completion of the reaction. The regenerated rubber was ejected of the vessel and cooled down. It is preferable to keep the regenerated rubber in continuous motion while cooling, in order to avoid degradation of the regenerated rubber. The regenerated rubber was, in some cases, cooled down using a screw type cooling device. The obtained regenerated rubber was slightly expanded, not oily, unmasticated, and non-sticky or non-tacky. It also had a characteristic velvet touch.

## Protocol B

A weighted quantity of scrap rubber from scrap tires in the form of a granulated powder, having a given size of 80, 100 or 120 mesh, was introduced into a vessel of the thermokinetic mixer type having a volume of 1 liter. The mixer is equipped  
5 with a temperature control system comprising a cooling jacket and with agitation means comprising a rotor having blades mounted on a central shaft and capable of generating high shearing forces. The thermokinetic energy generated by the agitation produce heat and the elastomer from scrap is thereby heated. The rotor blades were adequately designed and the agitation is carried out to avoid having stagnant particles of rubber in  
10 the vessel. Thus, all rubber powder was uniformly subjected to the combination of the thermal and mechanical energies. The rotor speed was set based on the quantity, type and granulometry of the rubber powder introduced into the vessel and at a sufficient level to generate high shearing forces. The powder was vigorously agitated for 30 seconds until it reached a temperature comprised between 140°C and 160°C. A tight control of the  
15 temperature was necessary during the process in order to prevent any damage to the powder in the form of degradation. When all the particles have reached the required temperature, a hot oil (aromatic oil, naphthenic oil or paraffinic oil ) having a temperature of about 190 to 200°C was added in a weight ratio, oil / rubber from scrap, comprised between 0.05 and 0.12. The ratio depends on the nature and the granulometry of the  
20 powder as well as on the type of oil selected and its temperature. The mixture was kept under agitation for a period of time of about 30 seconds to allow the completion of the reaction. The regenerated rubber was ejected of the vessel and cooled down. It is preferable to keep the regenerated rubber in continuous motion while cooling, in order to avoid degradation of the regenerated rubber. The regenerated rubber was, in some cases,  
25 cooled down using a screw type cooling device. The obtained regenerated rubber was slightly expanded, not oily, unmasticated, and non-sticky or non-tacky. It also had a characteristic velvet touch.

## Chemical and physical properties of the regenerated rubber

Laboratory tests revealed the presence of small amounts of free sulfur in the  
30 process of regenerating rubber that establishes that devulcanization has effectively taken place during the reaction using the process according to the present invention.

The tests conducted for testing the recycling ability of the rubbery mass obtained according to the process of the invention consist of using the following formulation:

	regenerated rubber	100 phr
5	zinc oxide	4 phr
	stearic acid	2 phr
	Delac® S	1 phr

With no sulfur added into the compound, a rheometer test carried out with a ViscoGraph from TechPro at a temperature of 150 °C, shows the typical curve of vulcanization. This is the evidence that some amount of free sulfur has effectively been released during the chemical treatment of the rubber particles. The devulcanization has involved the breakage of the C-S and S-S bonds that link the different rubber molecules. The devulcanization process is believed to be facilitated by the swelling action of the oil added into the rubber particles.

15 In addition, breakage of the main backbone chains at some locations is also believed to take place as the green strength and the mechanical properties of the regenerated mass are poorer than those of a virgin rubber of the same type as evidenced by tensile, elongation and tear properties.

Other tests have been performed to determine the quantity of oil lost during the process according to the first aspect of the invention. The weight of the reactants, rubber from scrap + oil, has been compared to the weight of the final product, the regenerated rubber, when using Protocol A. In a first experiment, a Goodyear 80 mesh EPDM from scarp was heated during 5 minutes until it reached the temperature of 152°C. Then a Shellflex oil at 199 °C was added in a weight ratio, oil / elastomer from scrap, of 0.08. The mixing time was 5 minutes. At the end of the process, the regenerated EPDM was obtained indicating a potential lost of oil of 0.6% by weight.

In a second experiment, a ROUSE 120 mesh EPDM from scarp was heated during 5 minutes until it reached the temperature of 153 °C. Then a Shellflex oil at 200 °C was added in a weight ratio, oil / elastomer from scrap, of 0.08. The mixing time was 5 minutes. At the end of the process, the regenerated EPDM was obtained indicating a potential lost of oil of 0.9 % by weight.

In a third experiment, a SIMCO 100 mesh EPDM from scarp was heated during 5 minutes until it reached the temperature of 160 °C. Then a Shellflex oil at 200 °C was added in a weight ratio, oil / elastomer from scrap, of 0.08. The mixing time was 5 minutes. At the end of the process, the regenerated EPDM was obtained indicating a potential lost of oil of 1.3 % by weight.

### Physical characterisation and analysis of compounds comprising regenerated rubber

The processing abilities and the mechanical properties have been evaluated by designing compounds based on the regenerated rubber. Basic compounds comprising regenerated rubber and virgin rubber at various proportions have been designed as shown below in Table 1. The regenerated SBR has been obtained according to Protocol A using 80 mesh SBR from scrap and Shellflex oil as starting material.

Table 1. Composition of Compounds 1 to 4 comprising virgin SBR and regenerated SBR.

Components	Compound 1 composition (%)	Compound 2 composition (%)	Compound 3 composition (%)	Compound 4 composition (%)
Regenerated SBR	25	50	75	100
SBR 1502	75	50	25	0
Carbon black	20	20	20	20
N330	4	4	4	4
Zinc oxide	2	2	2	2
Stearic acid	1.5	1.5	1.5	1.5
Delac NS	1.5	1.5	1.5	1.5
Sulfur				

The mixing operations for compounds 1 to 4 were carried out in a 5-liter Banbury mixer. All ingredients were added in the order listed above on a one-stage basis.

The mechanical properties of the cured compounds were evaluated with a tensile testing machine. Dumbbell shaped samples were die cut out of compression molded sheets. The curing conditions in the compression press were 10 minutes at 180 °C. The tensile properties and tear resistance were measured and compared to those of a compound based on virgin SBR rubber. The results are displayed in Table 2 for compounds containing 25, 50, 75 and 100 phr of regenerated rubber.

Table 2. Mechanical properties of Compounds 1 to 4.

Compounds	Concentration of regenerated rubber (phr)	Tensile Resistance psi	Elongation %	Tear Resistance Lb-ft	Hardness Shore A
Compound 4	100	711	78	79	75
Compound 3	75	1204	236	167	71
Compound 2	50	1678	456	239	62
Compound 1	25	1858	563	275	56

Further investigation on the effect of the parameters listed below on the mechanical properties of the regenerated rubber based compounds were evaluated.

The results are listed in tables 3.1 to 3.3.

## 3.1 Effects of conversion time on the mechanical properties

# COMPOUND	Time (min)	TENSILE (psi)	Elongation %	MOD 100% (psi)	MOD 200%	MOD 300%	TEAR Die C
2	4	1029.8	338.1	309.7	652.7	963.3	189.8
3	6	1026.1	395.4	326.8	593.1	853	207.2
2	10	1678.5	456.6	359.4	723.2	1124.1	239
4	14	817.3	371.6	301.2	534.9	721.8	188.6

## 3.2 Effect of the percentage of recycled rubber on the mechanical properties

# COMPOUND	% recycled	HARDNES Duro A	TENSILE (psi)	ELONGATION %	MOD 100%	MOD 200%	MOD 300%	TEAR Die C
1	25	55	1858.6	563.8	229.4	450.7	779	275.4
2	50	62	1678.5	456.6	359.4	723.2	1124.1	239
3	75	71	1204	236	600	1071		167.1
4	100	75	711.6	78.4				79

## 3.3 Effect of the conversion temperature on the mechanical properties

# COMPOUND	TEMPERATURE °C	TENSILE (psi)	ELONGATION %	MOD 100%	MOD 200%	MOD 300%	TEAR Die C
1	160	1378	275	355.9	966.1		199.9
2	170	1307.7	355.2	355.2	272.7	1131.7	198.6
3	180	1056.1	355.8	271	597.5	938	162.3
4	200	1678.5	456.6	359.4	723.2	1124.1	239



Compounds 5 and 6 are both compounds comprising virgin SBR and regenerated SBR. The Compound 5 comprises 25% by weight of regenerated SBR and compound 6 comprises 30% by weight of regenerated SBR. The regenerated SBR has been obtained according to Protocol A using 80 mesh SBR form scrap and Shellflex oil as starting material. Tables 4 to 6 illustrate results obtained with these compounds during several tests.

Table 4. Rheometer 191 C test for Compounds 5 and 6

PROPERTIES	Compound 5	Compound 6
Minutes	5.1	5.3
T rise	1.20	1.20
T25	1.48	1.43
S25	8.4	7.4
T90	2.33	3.38
S90	17.7	12.9
Max	19.1	13.8
Rate	10.93	2.86
AMT	14.0	8.5

Table 5. Scorch 121 C test for Compounds 5 and 6

PROPERTIES	Compound 5	Compound 6
INITIAL	33.6	35.8
MIN	18.9	19.6
T3	>20	>20

Table 6. Physical properties of Compounds 5 and 6

PROPERTIES	Compound 5	Compound 6
Tensile ultim. (psi)	1081	886
Modulus 100%	302	207
200%	547	378
300%	789	562
Elongation %	480.1	563
Hardness	65	62
Specific gravity	1.35	1.33

10 According to the following tables, Compounds 5 and 6 are acceptable for use in hose construction. No difficulties were encountered when applying Compounds 5 and 6 on a mandrel. The hose tube and cover surfaces appeared smooth and not granulated. The processing of Compound 5 on the mill and calender was achieved with success. The compounds were not sticky and they did not break down in crumbs. The

surface of these compounds was smooth and showed no evidence of surface defects. The surface was similar to standard product.

Compounds 7, 8 and 9 are compounds comprising virgin EPDM and regenerated EPDM. Compound 7 comprises 20% by weight of regenerated EPDM, Compound 8 comprises 30% by weight of regenerated EPDM and Compound 9 comprises 40% by weight of regenerated EPDM. The regenerated EPDM has been obtained according to Protocol A using 80 mesh EPDM form scrap and Sunpar 2280 oil as starting material. Tables 7 to 9 illustrate results obtained with these compounds during several tests.

10 Table 7. Rheometer 191 C test for Compounds 7, 8, and 9

Properties	Compound 7	Compound 8	Compound 9
Min	4.8	4.8	5.2
T rise	0.99	0.98	0.97
T25	1.30	1.27	1.23
S25	9.2	9.1	9.2
T90	2.00	1.91	1.85
S90	21.4	20.8	20.4
Max	23.2	22.5	22.1
Rate	17.31	18.22	18.05
AMT	18.4	17.7	16.9

Table 8. Scorch 121 C test for Compounds 7, 8, and 9

PROPERTIES	Compound 7	Compound 8	Compound 9
INITIAL	24.9	24.8	28.3
MIN	19.2	19.1	20
T3	>20	>20	>20

Table 9. Physical properties of Compounds 7, 8, and 9

PROPERTIES	Compound 7	Compound 8	Compound 9
Tensile ultim. (psi)	1109	1074	1035
Modulus 100%	348	350	350
200%	625	630	620
300%	832	838	831
Elongation %	539	518	493
Hardness	75	75	77
Specific gravity	1.23	1.23	1.22

According to the following tables, Compounds 7, 8 and 9 are acceptable for use in hose construction. No difficulties were encountered when applying these compounds on a mandrel. The hose tube and cover surfaces appeared smooth and not granulated. The processing of Compound 8 on the calender was achieved with success, it showed good tack on rolls, a smooth surface and it accepts anti-tack-dust. The surface of these compounds was smooth and showed no evidence of surface defects.

Tests have also been made in order to verify if it was necessary to add sulfur and accelerators to EPDM compounds comprising virgin EPDM and regenerated EPDM. The regenerated EPDM has been obtained according to Protocol A using 80 mesh EPDM form scrap and Sunpar 2280 oil as starting material. Compounds 10 to 21 are EPDM compounds comprising from 2.4 to 6.7% by weight of regenerated EPDM rubber and having a polymer content (EPDM) varying from 10 to 30% by weight. Compounds 10, 11, 16 and 17 comprise about 2.4 % by weight of regenerated EPDM and have a polymer content of about 10% by weight. Compounds 12, 13, 14, 18, 19 and 20 comprise about 4.8 % by weight of regenerated EPDM and have a polymer content of about 20% by weight. Compounds 15 and 21 comprise about 6.7% by weight of regenerated EPDM and have a polymer content of about 30% by weight. Compounds 10 to 15 have been prepared using 100 mesh regenerated EPDM and Compounds 16 to 21 have been prepared using 120 mesh regenerated EPDM. The results of these tests are showed in Tables 10 to 15. Cont represents a compound comprising virgin EPDM only and having a polymer content of about 23 % by weight.

Virgin EPDM rubber compound was banded on a 20 cm X 50 cm two-roll laboratory mill and the regenerated rubber was mixed in to it. Total milling time was about 10 minutes. The virgin material was passed through the mill 10 times with the gap narrowing after each two passes then banded and the regenerated material added. When the regenerated material was dispensed additional sulfur or curatives was added at this point. When all was dispersed the rubber was then pigged and passed through the mill 10 times sheeting it out on the last pass at approximately 100 thou in thickness.

Rheometer traces were obtained on an ODR at 150 °C, test plaques cured to (t<sub>80</sub>+ 5 minutes at 150 °C). After 24 hours specimens were die cut and tested using an Instron tensile tester.

Table 10. Composition of Compounds 10 to 15 comprising 100 mesh regenerated EPDM

	Cont	10	11	12	13	14	15
Virgin EPDM	500.0	500.0	500.0	500.0	500.0	500.0	500.0
Regenerated EPDM	-	12.0	12.0	24.0	24.0	24.0	36.0
MBTS	-	-	-	-	-	0.23	0.23
TMTD	-	-	-	-	-	0.35	0.35
Sulfur	-	-	0.3	-	0.3	0.23	0.23

Table 11. Rheometer data at 150 °C for Compounds 10 to 15

	Cont	10	11	12	13	14	15
Min. torque	4.0	4.1	4.1	5.1	4.7	5.8	5.3
Max. torque	40.3	38.7	43.6	40.3	44.9	47.5	46.9
Time to 2 pt. rise, min	5.0	4.3	3.8	4.0	3.8	3.8	3.8
Time to 90% cure, min	19.0	19.5	24.6	20.3	21.5	22.0	23.0

Table 12. Vulcanizate properties for Compounds 10 to 15 cured at 150 °C

	Cont	10	11	12	13	14	15
Hardness, Shore A	64	66	70	67	70	70	73
Modulus, psi 100 %	285	330	360	350	350	380	395
200%	525	640	710	660	675	710	710
300%	675	905	940	855	880	900	905
Tensile Strength, psi	990	1070	1165	1060	1110	1110	1110
Elongation at break, %	585	525	470	495	460	450	445
Tear Str., Die C, pli	227	252	195	230	197	221	215
Cure time, min	24	24.5	29.0	25.3	26.5	27.0	28.0

5 Table 13. Composition of Compounds 16 to 21 comprising 120 mesh regenerated EPDM

	Cont	16	17	18	19	20	21
Virgin EPDM	500.0	500.0	500.0	500.0	500.0	500.0	500.0
Regenerated	-	12.0	12.0	24.0	24.0	24.0	36.0
MBTS	-	-	-	-	-	0.23	0.23
TMTD	-	-	-	-	-	0.35	0.35
Sulfur	-	-	0.3	-	0.3	0.23	0.23

Table 14. Rheometer data at 150 °C for Compounds 16 to 21

	Cont	16	17	18	19	20	21
Min. torque	4.0	4.8	5.0	5.0	6.0	5.5	6.0
Max. torque	40.3	39.9	44.3	40.0	44.8	43.1	42.6
Time to 2 pt. rise,	5.0	4.8	4.3	4.5	4.0	4.0	4.0
Time to 90% cure.	19.0	19.0	21.5	20.5	18.5	16.8	15.8

Table 15. Vulcanizate properties for Compounds 16 to 21 cured at 150 °C

	Cont	16	17	18	19	20	21
Cure time, min	24	24.0	26.5	25.5	23.5	21.8	20.8
Hardness, Shore A	64	68	71	67	70	68	70
Modulus, psi 100%	285	310	352	325	335	355	340
200%	525	630	665	595	630	665	635
300%	675	825	855	775	820	855	825
Tensile Strength,	990	1090	1130	1015	1100	1090	1045
Elongation at	585	550	495	565	495	500	485
Tear Str., Die C pli	227	241	195	229	195	225	227

From Tables 10 to 12, it can be seen that when the polymer content was about 10% by weight (Compound 10) there was little change in viscosity, a slight drop in maximum torque and a slower cure rate. There was however a reduction in scorch safety. When additional sulfur was added, the maximum torque increased, cure rate and scorch safety decreased (Compound 11).

With the additional of the regenerated rubber itself, Compound 10, the hardness increased slightly; modulus, tensile strength and resistance to tearing increased while the elongation decreased but was still acceptable. Upon the addition of sulfur, in Compound 11, hardness and modulus increased further and tensile changed little, elongation decreased further, which then became less than the desired value and tear decreased. The scorch time decreased further as did the cure rate but in all cases was slower than the virgin compound.

Increasing the polymer content to 20% by weight (Compound 12) the viscosity and maximum torque increased, scorch safety decreased and cure rate slowed (Compound 12 vs. 10). The differences in property values were minor except hardness. However the elongation became marginally lower than desired but tear strength remained good. Additional sulfur produced only minor changes except for elongation and tear strength (Compound 13 vs. 12 ). Adding sulfur and accelerator produced minor changes (Compound 14 vs. 13 ) except tear became higher again. Compound 14 also had the highest viscosity and rheometer torque. Increasing the level to 30% by weight (Compound 15) did little except reduce elongation and increase hardness. The elongation is now well below the desired level.

In Tables 13 to 15, the trends of, both rheological and physical properties, are more or less the same as the results of Tables 10 to 12 although the scorch time

did not decrease as much and cure time was a little faster. Property values were quite similar. Modulus was slightly lower and elongation higher.

In view of the results of Tables 10 to 15, it does not appear overly necessary to add additional sulfur and accelerator to the compounds comprising virgin EPDM and regenerated EPDM. When adding these components, there is a reduction in scorch safety and elongation. Also with nothing else added but the regenerated material, the property values appear to be sufficient. The difference between nothing added and additional curatives is not all that large. In the presence of regenerated 120 mesh material, the properties appear to be slightly better than the 100 mesh material i.e. elongation and tear are better. The regenerated EPDM mixed well into the virgin EPDM and sheeted out well. Upon curing, the surface of regenerated EPDM is shiny and did not differ from the virgin.

Compounds 22 and 23 are SBR rubbers comprising virgin SBR and regenerated SBR. Compound A, used as a reference, comprises 173.89 phr of a virgin SBR. Compound 22 comprises 173.89 phr of a virgin SBR, 45 phr of a regenerated SBR and 10 phr of carbon black. Compound 23 comprises 173.89 phr of a virgin SBR, 45 phr of a regenerated SBR and 20 phr of carbon black. The regenerated SBR has been obtained using the process according to the Protocol A. The regenerated SBR has been obtained using 80 mesh SBR from scrap and naphtenic oil. The tests made on these compounds are illustrated in Table 16.

Table 16. Tests of Compounds 22 and 23

Property	Units	Compound A	Compound 22	Compound 23
Cure properties				
Max. torque	lb-in	67 - 87	50.00	59.52
Min. torque	lb-in	10 - 18	14.99	19.03
Ts(2)	min	0.90 - 1.18	1.01	0.88
Tc(80)	min	1.80 - 2.50	1.83	1.60
Viscosity				
MLI +4(100°C)	mooney	58 - 78	75.91	104.41
Physical properties				
Tensile	PSI	2700 min.	2246	2026
Elongation at break	%	308 - 438	345	298
Stress at 300% strain	PSI	2270-2950	2033	1996
Hardness	Shore A	79 - 87	82	84
Tear resistance die C	lbs/in	200 min	290	289
Abrasion resistance	mm <sup>3</sup>	101 (typical)	87	103
Flex life de Mattia	kilocycle	11 (typical)	13	11

The cure properties for Compound 22 are very similar to Compound A. Compound 22 even seems to cure slightly faster but with the same scorch safety. At lower temperatures the cure differences are amplified. At 166 °C Compound 22's Tc (80) is 5.41 minutes where Compound A's is around 7.5 minutes. Compound 22's viscosity is very interesting and should process well at the extruder. The physical properties demonstrated that Compound 22 should perform as well as a virgin SBR since it has similar properties than SBR. During experiments, it was demonstrated that the regenerated elastomer is compatible with the corresponding virgin elastomer and it has a similar polymer value. Thus, in elastomer compounds, the regenerated elastomer could replace a portion of the virgin elastomer normally used without affecting the properties of the compound. Finally, it proves the efficiency of the process according to the first aspect of the invention.

CLAIMS:

1. A process for converting an elastomer from scrap to a regenerated elastomer which comprises the steps of:

a) introducing the elastomer from scrap into a vessel equipped with agitating means, said elastomer from scrap being in a powder form;

b) agitating and heating said elastomer from scrap, limiting the heating of said elastomer from scrap to a temperature below the temperature where the elastomer begins to degrade;

c) introducing an oil into said vessel and admixing together the elastomer from scrap and the oil; and

d) cooling down the so formed regenerated elastomer, whereby the regenerated elastomer has properties similar to a corresponding virgin elastomer.

2. A process according to claim 1, wherein said vessel is equipped with a temperature control device comprising a heating system.

3. A process according to claim 2, wherein said temperature control device further comprises a cooling system.

4. A process according to any one of claims 1 to 3, wherein said agitating means comprises a rotor having at least one blade mounted on a central shaft.

5. A process according to claim 4, wherein the agitation of said elastomer from scrap is brought by rotating said rotor to generate shearing forces.

6. A process according to any one of claims 1 to 5, wherein the rotor is rotated at a revolution comprised between 150 and 1200 rpm.

7. A process according to claim 6, wherein the rotor is rotated at a revolution comprised between 160 and 200 rpm.



8. A process according to any one of claims 1 to 7, wherein said elastomer from scrap is converted to said regenerated elastomer in a period of time comprised between 30 seconds and 20 minutes.
9. A process according to claim 8, wherein said period of time is comprised between 5 minutes and 15 minutes.
10. A process according to claim 9, wherein said period of time is about 10 minutes.
11. A process according to any one of claims 1 to 10, wherein the vessel is a vessel of the double boiler type.
12. A process according to claim 11, wherein said boiler comprises a mixing chamber and a heating chamber.
13. A process according to any one of claims 1 to 3, wherein said elastomer from scrap is heated from the heat generated through thermokinetic energy produced by the agitation.
14. A process according to claim 13, wherein said agitating means comprise a rotor having at least one blade mounted in a central shaft.
15. A process according to claim 14, wherein the agitation of said elastomer from scrap is brought by rotating said rotor to generate shearing forces.
16. A process according to claim 14 or 15, wherein the rotor is rotated at a revolution comprised between 1500 and 3000 rpm.
17. A process according to claim 16, wherein the rotor is rotated at a revolution comprised between 1800 and 2000 rpm.
18. A process according to any one of claims 13 to 17, wherein said vessel is a mixer.

19. A process according to claim 18, wherein said mixer is a thermokinetic mixer
20. A process according to any one of claims 13 to 19, wherein said elastomer from scrap is converted to said regenerated elastomer in a period of time comprised between 30 seconds and 5 minutes.
21. A process according to claim 20, wherein said period of time is comprised between 45 seconds and 3 minutes.
22. A process according to claim 21, wherein said period of time is about 1 minute.
23. A process according to any one of claims 1 to 22, wherein said elastomer form scrap is heated at a temperature  $t_1$  comprised between 50 and 200 °C.
24. A process according to claim 23, wherein said temperature  $t_1$  is comprised between 140 and 170 °C.
25. A process according to claim 24, wherein said temperature  $t_1$  is about 160 °C.
26. A process according to any one of claims 1 to 25, wherein said powder has a particle size of about 15 to about 200 mesh.
27. A process according to claim 26, wherein said particle size is about 20 to about 120 mesh.
28. A process according to claim 27, wherein said particle size is about 80 to 100 mesh.
29. A process according to any one of claims 1 to 25, wherein the powder is constituted by at least 90 % of particles having a size of at least 15 mesh.
30. A process according to claim 29, wherein said particles have a size of at least 30 mesh.

31. A process according to any one of claims 1 to 25, wherein the powder is constituted by at least 99 % of particles having a size of at least 15 mesh.
32. A process according to claim 31, wherein said particles have a size of at least 30 mesh.
33. A process according to any one of claims 1 to 32, wherein said agitation is carried out to avoid having stagnant particles of said elastomer in the vessel.
34. A process according to any one of claims 1 to 33, wherein said agitation is carried out to evenly heat the elastomer from scrap and therefore prevent its degradation.
35. A process according to any one of claims 1 to 34, wherein said process has a weight ratio, oil / elastomer from scrap, comprised between 0.03 and 0.2.
36. A process according to claim 35, wherein said ratio is comprised between 0.04 and 0.14.
37. A process according to claim 36, wherein said ratio is comprised between 0.05 and 0.09.
38. A process according to any one of claims 1 to 37, wherein said oil is preheated prior to admixing.
39. A process according to any one of claims 23 to 25 wherein said oil is preheated, prior to admixing, at a temperature  $t_2$  being higher or equal to  $t_1$ .
40. A process according to claim 39, wherein the temperature  $t_2$  has a value comprised between  $t_1$  and  $t_1+60$  °C.
41. A process according to claim 40, wherein the temperature  $t_2$  has a value comprised between  $t_1+10$  and  $t_1+40$  °C.

42. A process according to any one of claims 1 to 41, wherein said oil is selected from the group consisting of synthetic oil, vegetable oil and mixtures thereof.

43. A process according to claim 42, wherein said oil is synthetic oil.

44. A process according to claim 43, wherein said synthetic oil is selected from the group consisting of aromatic oil, naphthenic oil, paraffinic oil and mixtures thereof.

45. A process according to claim 44, wherein said synthetic oil is paraffinic oil.

46. A process according to claim 45, wherein said elastomer from scrap is an ethylene propylene diene monomer rubber

47. A process according to claim 44, wherein said synthetic oil is aromatic oil or naphthenic oil.

48. A process according to claim 47, wherein said elastomer from scrap is a styrene butadiene rubber.

49. A process according to any one of claims 1 to 48, wherein said agitation is maintained during step (c).

50. A process according to any one of claims 1 to 48, wherein said agitation is maintained during steps (c) and (d).

51. A process according to any one of claims 1 to 48, wherein said process further comprises after step (b) and prior to step (c):

b') stopping said agitation

and said agitation is started again in step (c), after the introduction of the oil into said vessel.

52. A process according to any one of claims 1 to 51, wherein in step (d), the regenerated elastomer is kept in continuous motion in order to avoid degradation.

53. A process according to any one of claims 1 to 52, wherein said process further comprises after step (c) and prior to step (d):

c') ejecting said regenerated elastomer from said vessel.

54. A process according to claim 53, wherein step (d) is carried out using a screw type cooling device.

55. A process according to claim 54, wherein said screw type cooling device comprises a temperature control device.

56. A process according to any one of claims 1 to 55, wherein in step (d), said regenerated elastomer is cooled down to a temperature below 120°C to prevent its degradation.

57. A process according to claim 56, wherein said temperature is comprised between 90 and 120°C.

58. A process according to any one of claims 1 to 57, wherein said process is carried out in the presence of air.

59. A process according to any one of claims 1 to 57, wherein said process is carried out under an inert gas atmosphere.

60. A process according to claim 59, wherein said inert gas atmosphere is substantially free of oxygen.

61. A process according to claim 59 or 60, wherein said inert gas is argon or nitrogen.

62. A process according to any one of claims 59 to 61, wherein risks of a potential side reaction are reduced.

63. A process according to claim 62, wherein said side reaction is oxidation.
64. A process according to any one of claims 1 to 63, wherein no mastication of said elastomer from scrap occurs.
65. A process according to any one of claims 1 to 64, wherein no mastication of said regenerated elastomer occurs.
66. A process according to any one of claims 1 to 65, wherein the quantity of regenerated elastomer obtained at the end of said process corresponds to a value comprised between 97.0 and 99.9% of the combined weight of said elastomer from scrap and said oil introduced into the vessel.
67. A process according to claim 66, wherein said value is comprised between 98.5 and 99.5 % of the combined weight of said elastomer from scrap and said oil introduced into the vessel.
68. A process according to any one of claims 1 to 45, 47 and 49 to 67, wherein the elastomer from scrap is a rubber from scrap and the regenerated elastomer is a regenerated rubber.
69. A regenerated elastomer obtained by a process as defined in any one of claims 1 to 35 and 38 to 68.
70. A regenerated elastomer according to claim 69, wherein said regenerated elastomer is in a powder form.
71. A regenerated elastomer according to claim 70, wherein said regenerated elastomer has an aspect of expanded powder.

- 27 -

72. A regenerated elastomer according to claim 70 or 71, wherein said regenerated elastomer comprises a quantity of said oil comprised between 3 and 14 % by weight, the oil being encapsulated into said powder.

73. A regenerated elastomer according to claim 72, wherein the quantity of said oil is comprised between 5 and 8 % by weight.

74. A regenerated elastomer according to any one of claims 69 to 73, wherein said regenerated elastomer has a velvet touch and is non-sticky.

75. A regenerated elastomer according to any one of claims 69 to 74, wherein said regenerated elastomer does not retain moisture.

76. A regenerated elastomer according to any one of claims 69 to 75, wherein said regenerated elastomer does not soil hands by touch.

77. A regenerated elastomer according to any one of claims 69 to 76, wherein said regenerated elastomer is an unmasticated elastomer.

78. A regenerated elastomer according to any one of claims 69 to 77, wherein said regenerated elastomer exhibits all the required characteristics needed for processing by using the methods of mixing, molding, extrusion and calendering, commonly used in the rubber industry.

79. A regenerated elastomer obtained by a process as defined in claim 46, wherein said regenerated elastomer is effective in the composition of a product selected from the group consisting of gasket, hose and roofing.

80. A regenerated elastomer obtained by a process as defined in claim 48, wherein said regenerated elastomer is effective in the composition of hoses and car tires.

81. A regenerated rubber obtained by a process as defined in claim 68, wherein said rubber has a polymer content comprised between 10 and 40% by weight.

82. A regenerated rubber according to claim 81, wherein the polymer content is comprised between 25 and 35% by weight.

83. Use of the regenerated elastomer according to any one of claims 69 to 78 in the rubber industry.

84. Use according to claim 83, wherein the regenerated elastomer is, previously to its use in the rubber industry, prepared by a process selected from the group consisting of mixing, molding, extrusion, and calendering.

85. Use according to claim 83 or 84, wherein the regenerated elastomer is added with additives commonly used in the preparation of native rubber, previously to its use in the rubber industry.

86. Use of the regenerated elastomer according to any one of claims 69 to 78 in the composition of a product of the automobile industry.

87. Use according to claim 86, wherein said composition comprises between 1 and 40% by weight of said regenerated elastomer.

88. Use according to claim 87, wherein said composition comprises between 25 and 35% by weight of said regenerated elastomer.

89. Use of the regenerated elastomer according to any one of claims 69 to 78 in the fabrication of a hose.

90. Use according to claim 89, wherein said hose comprises between 1 and 40% by weight of said regenerated elastomer.

91. Use according to claim 90, wherein said hose comprises between 25 and 35% by weight of said regenerated elastomer.



92. Use of the regenerated elastomer according to any one of claims 69 to 78 in the fabrication of a gasket or a seal.

93. Use according to claim 92, wherein said gasket comprises between 1 and 40% by weight of said regenerated elastomer.

94. Use according to claim 93, wherein said gasket comprises between 25 and 35% by weight of said regenerated elastomer.

95. Use according to claim 92, wherein said seal comprises between 1 and 40% by weight of said regenerated elastomer.

96. Use according to claim 95, wherein said seal comprises between 25 and 35% by weight of said regenerated elastomer.